Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

IESI KEPURI									
Client :	The Lamine 22 Trewin S Wendouree	treet	Test Number : Issue Date : Print Date : Order Number:	20-00392 13/08/202 13/08/202 3455941	20				
Sample D	Description	•	ole 26212" with FR mineral & polymer core 7.3kg/m2						
AS/NZS 1530.3-1999		Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release							
		Face tested:	Decprative Face						
		Date tested:	13/08/2020						
			Standard Error	Mean					
		Ignition time	Nil	Nil	min				
		Flame propagation time	Nil	Nil	sec				
		Heat release integral	Nil	Nil	kJ/m²				
		Smoke release, log d	0.1190	-2.0198					
		Optical density, d		0.0111	/ metre				
		Number of specimens ignited:		0					
		Number of specimens tested:		6					
		Regulatory Indices:							
		Ignitability Index		0	Range 0-20				
		Spread of Flame Index		0	Range 0-10				
		Heat Evolved Index		0	Range 0-10				
		Smoke Developed Index		1	Range 0-10				

TEST REPORT

AWTA PRODUCT TESTING

211641

45786

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No. 983 985

1356

Page 1 of 2



MICHAEL A. JACKSON B.Sc.(Hons) MANAGING DIRECTOR

APPROVED SIGNATORY

12

C

AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	The Laminex Group Test N	Number	:	20-003924
	22 Trewin Street Issue	Date	:	13/08/2020
	Wendouree VIC 3355 Print I	Date	:	13/08/2020
	Order	r Number	r:	3455941

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen . A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was clamped along all sides.

211641

45786

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved (C)



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No : Accreditation No

985 1356

983



Page 2 of 2

MICHAEL A. JACKSON B.Sc.(Hons) ANAGING DIRECTOR